

ABSTRACT OF THE DISCLOSURE

A continuous polymerization process produces hydride-functional siloxane and organofunctional siloxane polymers, copolymers and terpolymers. The cationic polymerization takes place in a plug flow catalytic reactor packed with a heterogeneous acid catalyst. The siloxane polymers produced are optically clear, homogeneous and free of catalyst residues.